PRODUCT SPECIFICATION

Lastek B3020 V



Flux coated cadmium free silver brazing, brass colour

CLASSIFICATION

EN ISO 17672 : AG 220 EN 1044 : AG 206

GENERAL DESCRIPTION

Flux coated, cadmium free silver alloy, moderate silver content, for general maintenance. Suitable for joints with large clearances. For joining brass and other copper alloys, steel, stainless steel, cast iron and hard metal.

Good colour match with brass.

Operating temperature, up to 300 °C. // Melting range: 690-810 °C.

Lastek B3020V is cadmium free and applies to the European RoHS guideline and the European cadmium guideline.

APPLICATIONS

Machine parts for food and beverage industry.

Chandeliers, brass fittings and brass ornamental pieces.

Valves of bronze and brass.

Heat exchangers.

Automotive and electrical industry.

CHEMICAL COMPOSITION (%) (Typical values, all weld metal)

Cu : 43.00 - 45.00	Ag : 19.00 - 21.00	Zn : 34.00 - 38.00	Si : 0.05 - 0.25	

MECHANICAL PROPERTIES (Typical values, all weld metal)

Yield Strength	Tensile Strength	Elongation	Impact Strength
N/mm²	N/mm²	5d (%)	Charpy V notch (ISO-V)
NPD	330 MPa	NPD	NPD

GENERAL INFORMATION

Shielding gas NA Packing 1 kg in a cardboard box Polarity NA Diameter (mm) 1.5 2.0 3.0 Lenght (mm) 500 500 500	Welding positions	PA, PB							
Polarity NA Diameter (mm) 1.5 2.0 3.0	Shielding gas	NA							
Diameter (mm) 1.5 2.0 3.0	Packing	1 kg in a cardboard box							
· ,	Polarity	NA							
Lenght (mm) 500 500 500	Diameter (mm)	1.5	2.0	3.0					
	Lenght (mm)	500	500	500					

Tips & tricks Joint preparation: optimum clearances 0.05 to 0.20 mm.

Preheat the work piece slightly with neutral flame. Rub the coated rod along the joint to apply the flux. As soon as the flux is flowing, melt the rod. Continue heating until the alloy flows into the entire joint by capillarity.

Cool down and remove flux residues by brushing with hot water.

The information in this document is based on intensive tests and is accurate to the best of our knowledge. Do note that these values are only typical values for tests in accordance to prescribed standards. The suitability of the product should always be confirmed by qualification tests before use in any application. The information can be changed without previous notice.

PSEN_LB3020V_N0525_TW